BEYOND ASIAN HUB, TOWARD GLOBAL WORLD

KTR KOREA TESTING & RESEARCH INSTITUTE

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea TEL 82-43-211-6144 FAX 82-43-211-6148

Report No : TAK-2025-050995
Representative : LEE JIN WON
Company name : HYUNDAI L&C
Address : 1077, Cheonho-daero, Gangdong-gu, Seoul, Republic of Korea

Receipt Date : 2025.04.01.
Test Completion Date : 2025.04.25.

Sample name : Hanex_Trio

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Specific Gravity((23/23) ℃)(Method A)	-	-	1.72	ASTM D792-20
Rockwell Hardness(HRM)(Procedure A)	-	-	108	ASTM D785-08(2015)
Tensile Strength(**)	MPa	-	34.8	ASTM D638-22
Tensile Modulus of Elasticity(**)	GPa	-	8.44	ASTM D638-22
Flexural Strength(***)	MPa	-	57.6	ASTM D790-17
Flexural Modulus of Elasticity(***)	GPa	-	10.4	ASTM D790-17
Izod Impact Strength(Method A)	J/m	-	17	ASTM D256-23e1
Water Absorption(24 h Immersion)	%	-	0.02	ASTM D570-22
Density(23 ℃)(Method A)	kg/m^3	-	1.72×10^3	ASTM D792-20
Heat Resistance(Appearance)	-	-	No Defects	applied JIS K 6902 : 2022(Method B)
Hot Water Resistance(Appearance)	-	-	No Defects	applied JIS K 6902 : 2022(Method B)
Deflection Temperature Under Load(1.82 MPa, Method B)	℃	-	103	ASTM D648-18
Thermal Expansion	1/℃	-	4.3×10^{-5}	applied KS M 3015 : 2003

** Specimen: Type III, Speed of Testing: 5 mm/min(Modulus: 1 mm/min)
*** Support Span: 194 mm, Speed of Testing: 5.2 mm/min
- Usage of Report : QUALITY CONTROL

- Next Page -

LEE CHAN GOO
Prepared by LEE CHAN GOO
Tel : 02-2092-3647

Kyoung-Mun KIM
Reviewed by Kyoung-Mun KIM
Tel : 1577-0091(ARS ①→④)

2025.04.25

Korea Testing & Research Institute

President Kim Hyun cheol

QR Code for forgery

KTR KOREA TESTING & RESEARCH INSTITUTE

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea TEL 82-43-211-6144 FAX 82-43-211-6148

Report No : TAK-2025-050995
Representative : LEE JIN WON
Company name : HYUNDAI L&C
Address : 1077, Cheonho-daero, Gangdong-gu, Seoul, Republic of Korea

Receipt Date : 2025.04.01.
Test Completion Date : 2025.04.25.

Sample name : Hanex_Trio

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD

- End of Report -

Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

COPY ONLY

L E E C H A N G O O

Prepared by LEE CHAN GOO
Tel : 02-2092-3647

Kyoung-Mun KIM

Reviewed by Kyoung-Mun KIM
Tel : 1577-0091(ARS ①→④)

2025.04.25

Korea Testing & Research Institute

President Kim Hyun cheol

QR Code for forgery