

TEST REPORT

APPLICANT : HYUNDAI L&C

REPORT NO. : D270-26-00031

SAMPLE RECEIVED DATE : 2026-01-21

REPORT ISSUED DATE : 2026-02-04

PAGE : 1 OF 2

SAMPLE NAME SUBMITTED BY THE APPLICANT : BODAQ INTERIOR FILM

TEST CONDUCTED : As requested by the applicant, for details please see attached page(s).

PREPARED AND CHECKED BY
FOR FITI

Jong Seon Kim

JONG SEON, KIM
QUALITY MANAGER

AUTHORIZED BY
FOR FITI

Yun Ju KEYNG

JU-KEYNG YUN
PRESIDENT

※ Report Verification No.: Y98X-XM8E-6EWQ ※

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)



REPORT NO.: D270-26-00031

PAGE : 2 OF 2

01. RESISTANCE TO HEAT (CLIENT'S REQUEST METHOD) : mm

	#1
LENGTH	1.706
WIDTH	0.083

NOTE) PRE-TREATMENT CONDITION : (60 ± 1) °C, 48 h → (23 ± 2) °C, (50 ± 5) % R.H., 24 h

SPECIMEN SIZE : 100 mm X 100 mm

TEST METHOD : AFTER PRE-TREATMENT BY MAKING A CROSSWISE OF 100 mm CUT IN THE CENTER OF THE TEST SPECIMEN, THE MAXIMUM GAP OF THE CUT IS MEASURED WITH A LIGHT MICROSCOPE.

THE TEST WAS CONDUCTED AFTER REMOVING THE RELEASE PAPER.

**** End of The Report ****

- SAMPLE PHOTO -

