

TEST REPORT

APPLICANT : HYUNDAI L&C

REPORT NO. : D270-26-00033

SAMPLE RECEIVED DATE : 2026-01-21

REPORT ISSUED DATE : 2026-02-04

PAGE : 1 OF 2

SAMPLE NAME SUBMITTED BY THE APPLICANT : BODAQ INTERIOR FILM

TEST CONDUCTED : As requested by the applicant, for details please see attached page(s).

PREPARED AND CHECKED BY
FOR FITI

Jong Seon Kim

JONG SEON, KIM
QUALITY MANAGER

AUTHORIZED BY
FOR FITI

Yun Ju KEYNG

JU-KEYNG YUN
PRESIDENT

※ Report Verification No.: VMJ6-ACX5-KXHE ※

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)



REPORT NO.: D270-26-00033
PAGE : 2 OF 2

01. TENSILE STRENGTH (KS T 1028 : 2018) : N/10 mm

	#1
LENGTH	48.6
WIDTH	45.1

NOTE) THE TEST WAS CONDUCTED AFTER REMOVING THE RELEASE PAPER.
THE TEST WAS CONDUCTED BOTH DIRECTIONS BY THE CLIENT'S REQUEST.

02. ELONGATION (KS T 1028 : 2018) : %

	#1
LENGTH	212
WIDTH	226

NOTE) THE TEST WAS CONDUCTED AFTER REMOVING THE RELEASE PAPER.
THE TEST WAS CONDUCTED BOTH DIRECTIONS BY THE CLIENT'S REQUEST.

03. TEARING STRENGTH (KS T 1028 : 2018) : N

	#1
LENGTH	3.92
WIDTH	5.34

NOTE) THE NUMBER OF SHEETS TORN SIMULTANEOUSLY: 1
THE TEST WAS CONDUCTED AFTER REMOVING THE RELEASE PAPER.

04. ADHESION STRENGTH (KS T 1028 : 2018) : N/10 mm

	#1
	8.76

NOTE) TEST METHOD : SINGLE-COATED TAPES AT 180° ANGLE
REAGENT FOR CLEANING TEST PANEL : ETHANOL
COMPRESSION SPEED : 300 mm/min
COMPRESSION CYCLE : 1 CYCLE
DWELL TIME : 5 min

**** End of The Report ****

- SAMPLE PHOTO -

