

# TEST REPORT



APPLICANT : HYUNDAI L&amp;C

REPORT NO. : D270-26-00032

SAMPLE RECEIVED DATE : 2026-01-21

REPORT ISSUED DATE : 2026-03-04

PAGE : 1 OF 2


=====

SAMPLE NAME SUBMITTED BY THE APPLICANT : BODAQ INTERIOR FILM

=====

TEST CONDUCTED : As requested by the applicant, for details please see attached page(s).

=====

PREPARED AND CHECKED BY  
FOR FITIJONG SEON, KIM  
QUALITY MANAGERAUTHORIZED BY  
FOR FITIJU-KEYNG YUN  
PRESIDENT

※ Report Verification No.: BYSH-FS6V-IY6C ※

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)

## e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KS Q ISO/IEC 17025 and KOLAS accreditation.

Only the original report (including reissue) is valid. The test report received via e-mail(including its copy and the file) is an e-document for reference of test results and is NOT the official Document.

REPORT NO.: D270-26-00032

PAGE : 2 OF 2

# 01. ASSESSMENT OF SURFACE RESISTANCE ( KS G ISO 4211 : 2009 ) : NUMERICAL RATING CODE

|                        | #1                    |
|------------------------|-----------------------|
| ACETIC ACID            | NO VISIBLE CHANGES(5) |
| ACETONE                | DRASTIC CHANGES(1)    |
| AMMONIA SOLUTION       | NO VISIBLE CHANGES(5) |
| GRAPE JUICE            | NO VISIBLE CHANGES(5) |
| CITRIC ACID            | NO VISIBLE CHANGES(5) |
| CLEANSING AGENT        | NO VISIBLE CHANGES(5) |
| COFFEE                 | NO VISIBLE CHANGES(5) |
| DISINFECTANT           | NO VISIBLE CHANGES(5) |
| ENDORSING INK          | NO VISIBLE CHANGES(5) |
| ETHANOL, NON DENATURED | NO VISIBLE CHANGES(5) |
| ETHYL-BUTYL ACETATE    | DRASTIC CHANGES(1)    |
| MILK, CONDENSED        | NO VISIBLE CHANGES(5) |
| OLIVE OIL              | NO VISIBLE CHANGES(5) |
| PARAFFIN OIL           | NO VISIBLE CHANGES(5) |
| SBP SPIRIT             | NO VISIBLE CHANGES(5) |
| SODIUM CARBONATE       | NO VISIBLE CHANGES(5) |
| SODIUM CHLORIDE        | NO VISIBLE CHANGES(5) |
| TEA                    | NO VISIBLE CHANGES(5) |
| WATER                  | NO VISIBLE CHANGES(5) |

NOTE) SUBCONTRACTOR : KOREA ARCHITECTURE SAFETY TESTING&RESEARCH INSTITUTE  
(CERTIFICATE NO. : RC2602-0153(2026.02.10.) )

**\*\* End of The Report \*\***



## e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KS Q ISO/IEC 17025 and KOLAS accreditation. Only the original report (including reissue) is valid. The test report received via e-mail(including its copy and the file) is an e-document for reference of test results and is NOT the official Document.